

Thermal Conductivity	201 W/m. K
Density	2.75g/cm <sup>3</sup>
Young modulus	None
yield Strength	≥240 mpa
Ultimate tensile strength	≥290 mpa
Elongation	δ 5 (%) : ≥9
Hardness	75~90HB